

Dec. 2, 2004 1:46PM OP Fay Sharpen POSITION FOR THE FORMATION No. 25072F, P. 6.D  
**ULTRAVIOLET-ABSORBING AND HEAT-REFLECTING GLASS MADE BY USING THE  
SAME**  
EPA 99-02 0890556 NDN-050-0060-6308-1

**INVENTOR(S)**- NAKAMURA, K. Nippon Sheet Gl. Co., Ltd. 5-11, Doshomachi 3-chome, Chuo-ku Osaka-shi  
Osaka-fu 541 JP  
**INVENTOR(S)**- MAEDA, Koichi Nippon Sheet Gl. Co., Ltd. 5-11, Doshomachi 3-chome, Chuo-ku Osaka-shi  
Osaka-fu 541 JP

**APPLICANT(S)**- Nippon Sheet Glass Co., Ltd. (619688) 5-11, Doshomachi 3-chome, Chuo-ku Osaka-  
shi, Osaka-fu 541 JP **DESG. COUNTRIES**- BE; DE; FR; GB; IT  
**PATENT APPLICATION NUMBER**- 97950387  
**DATE FILED**- 1997-12-25  
**PUBLICATION NUMBER**- 00890556/EP A1  
**PUBLICATION DATE**- 1999-01-13  
**PATENT PRIORITY INFO**- JP. 344799/96, 1996-12-25  
**ATTORNEY, AGENT, OR FIRM**- Allen, Philippa Margaret et al, (73171), Markgraaf Patents Limited The  
Crescent 54 Blossom Street, York YO24 1AP, GB  
**INTERNATIONAL PATENT CLASS**- C03C01723; C03C01727  
**PCT APP. NO.**- 9704812/J PCT  
**PCT PUB. NO.**- 98029352/WO

**PCT PUB. DATE**- 1998-07-09  
**PUBLICATION**- 1999-01-13, A1, Published application with search report  
**FILING LANGUAGE**- Japanese  
**PROCEDURE LANGUAGE**- English  
**LANGUAGE**- English

The present invention relates to an optical thin film containing titanium oxide, cerium oxide and bismuth oxide, wherein the content ratio of the titanium oxide, cerium oxide, and bismuth oxide is within the area expressed by four-cornered shape ABCD consisting of A (4,1.95), B (98,1.1), C (20.79,1), and D (3,14.83) in term of coordinate points (TiOsub2 mol percent, CeOsub2 mol percent, and Bisub2Osub3 mol percent) of the mol ratio when being converted to oxides of TiOsub2, CeOsub2, and Bisub2Osub3. Furthermore, with the invention, a comparatively high refractive index film layer and a comparatively low refractive index film layer are alternately laminated at least three layers on a transparent glass substrate, at least two layers of said three layers are high refractive index films, and at least one layer of said high refractive index films is said optical thin film. Therefore, the invention provides an optical thin film having a high refractive index to increase a thermic ray reflection selecting performance and having ultraviolet ray absorption performance, and provides ultraviolet ray absorbing and thermic ray reflecting glass using the same.